



Declaration of Performance

N°CHIMFORTKEM_H_01A_EN

DoP num. kemhybrid

Bonded anchor resin in cartridge



1. Identification of the product: **KEM HYBRID – KEM H**

2. Identification code (art. 11.4), for the batch or serial number see packaging:

Type of Cartridge	Format	Cod.
Coaxial	280 - 380 ml	344 616 000 – 344 617 000

3. Intended use:

Generic type	Bonded anchor for anchorage of Threaded Rod and Rebar as ETA-16/0957
Base Material	Concrete C20/25 to C50/60 acc. to EN206-1
Use category	<ul style="list-style-type: none"> ▪ Installation in dry and wet concrete (not flooded boreholes) ▪ Overhead installation
Material & Durability	<ul style="list-style-type: none"> ▪ Threaded rod Galvanized cl.4.6 to cl.8.8 acc. to EN ISO898 for dry internal conditions ▪ Threaded rod Stainless Steel cl. A4-70 acc. to EN ISO3506 for internal and external use without particular aggressive conditions ▪ Threaded rod High Resistant Stainless Steel HCR-70 acc. to EN ISO3506 for all conditions ▪ Rebar Class B and C as EN 1992-1-1:2004+AC:2010, Annex C
Loading	Static, quasi-static and Seismic load
Temperature Range	<ul style="list-style-type: none"> ▪ 40°C to +80°C max long term temperature +50°C and max short term temperature +80°C ▪ -40°C to +120°C max long term temperature +72°C and max short term temperature +120°C ▪ -40°C to +160°C max long term temperature +100°C and max short term temperature +160°C
Fire Reaction	A1 according to EN 13501-1

Generic type	Bonded anchor for anchorage of Post-Installed Rebar Connection as ETA-16/0961
Base material	Non-carbonated Concrete C12/15 to C50/60 acc. to EN206-1 [max 0,4 % CL]
Use category	<ul style="list-style-type: none"> ▪ Installation in dry and wet concrete (not flooded boreholes) ▪ Overlap joint with existing reinforcement in a building component ▪ Anchoring of the reinforcement at a slab or beam support ▪ Anchoring of reinforcement of building components stressed primarily in compression ▪ Anchoring of reinforcement to cover the envelope line of tensile force in the bending member
Material & Durability	<ul style="list-style-type: none"> ▪ Rebar Class B and C as EN 1992-1-1:2004+AC:2010, Annex C ▪ ZA Tension Anchor B500 B as DIN 488 for internal and external use without particular aggressive conditions ▪ ZA Tension Anchor Stainless Steel A4 as DIN 488 for internal and external use without particular aggressive conditions ▪ ZA Tension Anchor High Resistance Stainless Steel HCR as DIN 488 for all conditions
Loading	Static, quasi-static and Fire exposure as EN1992-1
Temperature Range	<ul style="list-style-type: none"> ▪ -40°C to +80°C max long term temperature +50°C and max short term temperature +80°C
Fire Reaction	A1 according to EN 13501-1

4. Manufacturer (art. 11.5): **Friulsider SpA via trieste,1 - 33048 San Giovanni al Natisone (UD) - Italy**

5. Authorised representative (art. 12.2): **Not Relevant**

6. System of Assessment AVCP (annex V): **System 1**


7/8. Harmonised Specification & Notified Body:

	Name of Body	System of Assessment	Reference	EAD / hEN Document
Technical Specification Document	DiBt ^[TAB]	1	ETA-16/0957	ETAG001 p.1-5
Constancy of Performance & FPC	MPA Darmstadt 1343 ^[NB]	1	1343-CPR-M 527-9	ETAG001 p.1-5
Technical Specification Document	DiBt ^[TAB]	1	ETA-16/0961	EAD 330087-00-0601
Constancy of Performance & FPC	MPA Darmstadt 1343 ^[NB]	1	1343-CPR-M 527-8	EAD 330087-00-0601

9. Declared Performance: **See Annexes**

10. The performance of the product identified in points 1 and 2 is in conformity with declared performance in point 9.
This declaration of performance is issued under the sole responsibility of Friulsideer SpA.

Signed for and behalf of the manufacturer by:

Function	Name	Signature	Place and date of issue
Chef de produits	Damien Loizelle		Le Pecq, 18.12.2018

ANNEX I°

Declared Performances acc. to ETA-16/0957 & ETAG001 p.1-5 - Design method acc. to TR029 or CEN/TS 1992-4 Declared Performances acc. to ETA-16/0957 & ETAG001 Annex E - Design method acc. to TR045

ESSENTIAL CHARACTERISTICS			PERFORMANCE - THREADED RODS								
Installation parameters			d	M8	M10	M12	M16	M20	M24	M27	M30
d_0	Nominal diameter of drill bit	[mm]		10	12	14	18	22	28	30	35
h_{ef}	Effective embedment depth	$h_{ef,min}$	[mm]	60	60	70	80	90	96	108	120
		$h_{ef,std}$	[mm]	80	90	110	125	170	210	240	270
		$h_{ef,max}$	[mm]	160	200	240	320	400	480	540	600
h_{min}	Minimum thickness of the concrete member	[mm]	$h_{ef} + 30 \geq 100$				$h_{ef} + 2 \cdot d_0$				
T_{inst}	Torque moment (max)	[Nm]		10	20	40	60	100	170	250	300
s_{min}	Minimum spacing	[mm]		40	50	60	75	95	115	125	140
c_{min}	Minimum edge distance	[mm]		35	40	45	50	60	65	75	80
TENSION Steel failure											
$N_{Rk,s}$	Tension Steel characteristic failure	cl. 4.8 - 4.6	[kN]	15	23	34	63	98	141	184	224
		cl. 5.8 - 5.6	[kN]	18	29	42	78	122	176	230	280
		cl. 8.8	[kN]	29	46	67	125	196	282	368	449
		A4-70 (50)	[kN]	26	41	59	110	171	247	(230)	(281)
$\gamma_{m,sN}^{1)}$	Partial safety factor	cl. 4.6-5.6	[-]	2,0							
		cl. 4.8-5.8-8.8	[-]	1,5							
		A4-70 (50)	[-]	1,87							(2,86)
Combined pull-out and concrete failure											
$\tau_{Rk,ucr}$	Characteristic bond resistance for un-cracked concrete C20/25	80°/50°C	[MPa]	17	17	16	15	14	13	13	13
		120°/72°C	[Mpa]	15	14	14	13	12	12	11	11
		160°/100°C	[MPa]	12	12	11	10	9,5	9	9	9
$\tau_{Rk,cr}$ $\tau_{Rk,seisC1}$	Characteristic bond resistance for cracked concrete C20/25 and Seismic Category C1	80°/50°C	[MPa]	6,5	7	7,5	8,5	8,5	8,5	8,5	8,5
		120°/72°C	[Mpa]	5,5	6	6,5	7,5	7,5	7,5	7,5	7,5
		160°/100°C	[MPa]	5	5,5	6	6,5	6,5	6,5	6,5	6,5
$\tau_{Rk,seisC2}$	Characteristic bond resistance for Seismic Category C2	80°/50°C	[MPa]	-	-	3,6	-	-	-	-	-
		120°/72°C	[Mpa]	-	-	3,1	-	-	-	-	-
		160°/100°C	[MPa]	-	-	2,5	-	-	-	-	-
ψ_c	Increasing factor for concrete	C30/37	[-]	1,07							
		C40/50	[-]	1,08							
		C50/60	[-]	1,10							
$k_{g,cr}$	Factor acc. to CEN/TS 1992-4-5 sec.6.2.2.3 cracked	[-]	7,2								
$k_{g,ucr}$	Factor acc. to CEN/TS 1992-4-5 sec.6.2.2.3 un-cracked	[-]	10,1								
Concrete cone failure											
K_{cr}	Factor acc. to CEN/TS 1992-4-5 sec.6.2.3.1 cracked	[-]	7,2								
K_{ucr}	Factor acc. to CEN/TS 1992-4-5 sec.6.2.3.1 un-cracked	[-]	10,1								
$c_{cr,N}$	Critical edge distance	[mm]	$1,5 \cdot h_{ef}$								
$s_{cr,N}$	Critical spacing	[mm]	$3,0 \cdot h_{ef}$								
Splitting failure											
$c_{cr,sp}$	Critical edge distance for Splitting	$h / h_{ef} \geq 2,0$	[mm]	$1,0 \cdot h_{ef}$							
		$2,0 > h / h_{ef} > 1,3$	[mm]	$2,0 \cdot h_{ef} \cdot (2,5 - h / h_{ef})$							
		$h / h_{ef} \leq 1,3$	[mm]	$2,4 \cdot h_{ef}$							
$s_{cr,sp}$	Critical spacing for Splitting	[mm]	$2,0 \cdot c_{cr,sp}$								
$\gamma_2 = \gamma_{inst}$	Installation safety factor for Cleaning CAC ¹⁾	[-]	1,0 [1,2 for cracked]					1,2			
$\gamma_2 = \gamma_{inst}$	Installation safety factor for Cleaning MAC ¹⁾	[-]	1,2					-			
Displacement under Tension Load in Concrete 2)											
δ_{N0}	Short term displacement un-cracked concrete	80°/50°C	[mm/MPa]	0,031	0,032	0,034	0,037	0,039	0,042	0,044	0,046
		120°/72°C	[mm/MPa]	0,032	0,034	0,035	0,038	0,041	0,044	0,046	0,048
		160°/100°C	[mm/MPa]	0,121	0,126	0,131	0,142	0,153	0,163	0,171	0,179
$\delta_{N\infty}$	Long term displacement un-cracked concrete	80°/50°C	[mm/MPa]	0,040	0,042	0,044	0,047	0,051	0,054	0,057	0,060
		120°/72°C	[mm/MPa]	0,042	0,044	0,045	0,049	0,053	0,056	0,059	0,062

δ_{N0}	Short term displacement cracked concrete and Seismic C1	160°/100°C	0,124	0,129	0,135	0,146	0,157	0,168	0,176	0,184
		80°/50°C	0,081	0,083	0,085	0,090	0,095	0,099	0,103	0,106
		120°/72°C	0,084	0,086	0,088	0,093	0,098	0,103	0,107	0,110
		160°/100°C	0,312	0,321	0,330	0,349	0,367	0,385	0,399	0,412
$\delta_{N\infty}$	Long term displacement cracked concrete and Seismic C1	80°/50°C	0,104	0,107	0,110	0,116	0,122	0,128	0,133	0,137
		120°/72°C	0,108	0,111	0,114	0,121	0,127	0,133	0,138	0,143
		160°/100°C	0,321	0,330	0,340	0,358	0,377	0,396	0,410	0,424
		All range temperature	-	-	0,120	-	-	-	-	-
δ_{N0}	Short term displacement Seismic C2	[mm/MPa]	-	-	0,120	-	-	-	-	
$\delta_{N\infty}$	Long term displacement Seismic C2		-	-	0,140	-	-	-	-	

¹⁾ CAC = Cleaning with Compressed air and MAC = Cleaning with Manual Hand Pump

²⁾ Calculation of the displacement = $\delta_N \times \tau$ ($\tau = \tau_{rk} / \gamma_2 \times 1,5 \times 1,4$)

ANNEX II°

Declared Performances acc. to ETA-16/0957 & ETAG001 p.1-5 - Design method acc. to TR029 or CEN/TS 1992-4
Declared Performances acc. to ETA-16/0957 & ETAG001 Annex E - Design method acc. to TR045

ESSENTIAL CHARACTERISTICS			PERFORMANCE - THREADED RODS							
SHEAR Steel failure			M8	M10	M12	M16	M20	M24	M27	M30
$V_{Rk,s}$	Shear Steel characteristic failure	cl. 4.8 - 4.6 [kN]	7	12	17	31	49	71	92	112
		cl. 5.8 - 5.6 [kN]	9	15	21	39	61	88	115	140
		cl. 8.8 [kN]	15	23	34	63	98	141	184	224
		A4-70 (50) [kN]	13	20	30	55	86	124	(115)	(140)
$V_{Rk,s,C1}$	Shear Steel characteristic failure Seismic C1	[kN]	0,70 • $V_{Rk,s}$							
$V_{Rk,s,C2}$	Shear Steel characteristic failure Seismic C2	[kN]	-	-	0,70 • $V_{Rk,s}$	-	-	-	-	-
$M^0_{Rk,s}$	Characteristic Bending Moment	cl. 4.8 - 4.6 [Nm]	15	30	52	133	260	449	666	900
		cl. 5.8 - 5.6 [Nm]	19	37	65	166	324	560	833	1123
		cl. 8.8 [Nm]	30	60	105	266	519	896	1333	1797
		A4-70 (50) [Nm]	26	52	92	232	454	784	(832)	(1125)
$M^0_{Rk,s,C1}$	Characteristic Bending Moment Seismic C1	[kN]	NPD [No Performance Data]							
$M^0_{Rk,s,C2}$	Characteristic Bending Moment Seismic C2	[kN]	NPD [No Performance Data]							
$\gamma_{m,sV}$	Partial safety factor	cl. 4.6-5.6 [-]	1,67							
		cl. 4.8-5.8-8.8 [-]	1,25							
		A4-70 (50) [-]	1,56							(2,38)
K_2	Ductility factor acc. to CEN/TS 1992-4-5 sec.6.3.2.1	[-]	0,8							
Concrete pry-out failure										
k	Factor in equation 5.7 of TR029	[-]	2,0							
K_3	Factor in equation 27 of CEN/TS 1992-4-5 sec.6.3.3	[-]	1,0							
$\gamma_2 = \gamma_{inst}$	Installation safety factor	[-]	1,0							
Concrete edge failure			<i>see CEN/TS 1992-4-5 Section 6.3.4</i>							
l_f	Effective length of anchor	[-]	$l_f = \min(h_{ef}, 8 \cdot d_{nom})$							
d_{nom}	Outside diameter of anchor	[mm]	8	10	12	16	20	24	27	30
$\gamma_2 = \gamma_{inst}$	Installation safety factor	[-]	1,0							
Displacement under Shear Load ¹⁾			M8	M10	M12	M16	M20	M24	M27	M30
δ_{V0}	Short term displacement in Concrete and Seismic C1	[mm/kN]	0,06	0,06	0,05	0,04	0,04	0,03	0,03	0,03
$\delta_{V\infty}$	Long term displacement in Concrete and Seismic C1		0,09	0,08	0,08	0,06	0,06	0,05	0,05	0,05
δ_{V0}	Short term displacement for Seismic C2 action	[mm/kN]	-	-	0,27	-	-	-	-	-
$\delta_{V\infty}$	Long term displacement for Seismic C2 action		-	-	0,27	-	-	-	-	-

¹⁾ Calculation of the displacement = $\delta_v \times V$ ($V = V_{Rk,s} / \gamma_2 \times 1,5 \times 1,4$)

ANNEX III°

Declared Performances acc. to ETA-16/0957 & ETAG001 p.1-5 - Design method acc. to TR029 or CEN/TS 1992-4

Declared Performances acc. to ETA-16/0957 & ETAG001 Annex E - Design method acc. to TR045

ESSENTIAL CHARACTERISTICS			PERFORMANCE - REBAR								
Installation parameters			Ø8	Ø10	Ø12	Ø14	Ø16	Ø20	Ø25	Ø28	Ø32
d₀	Nominal diameter of drill bit	[mm]	12	14	16	18	20	25	32	35	40
h_{ef}	Effective embedment depth	h _{ef,min} [mm]	60	60	70	75	80	90	100	112	128
		h _{ef,std} [mm]	80	90	110	115	125	170	210	250	280
		h _{ef,max} [mm]	160	200	240	280	320	400	480	540	640
h_{min}	Minimum thickness of the concrete member	[mm]	h _{ef} + 30 ≥ 100		h _{ef} + 2 • d ₀						
s_{min}	Minimum spacing	[mm]	40	50	60	70	75	95	120	130	150
c_{min}	Minimum edge distance	[mm]	35	40	45	50	50	60	70	75	85
TENSION Steel failure											
N_{Rk,s}	Tension Steel characteristic failure	[kN]	A _s • f _{uk} ²⁾								
A_s	Area resistant	[mm ²]	50	79	113	154	201	214	491	616	804
γ_{m,sN}	Partial safety factor	[-]	1,4 ³⁾								
Combined pull-out and concrete cone failure			Ø8	Ø10	Ø12	Ø14	Ø16	Ø20	Ø25	Ø28	Ø32
τ_{Rk,ucr}	Characteristic bond resistance in un-cracked concrete C20/25	80°/50°C [MPa]	14	14	14	14	13	13	13	13	13
		120°/72°C [MPa]	13	12	12	12	12	11	11	11	11
		160°/100°C [MPa]	10	10	9,5	9,5	9,5	9	9	9	9
τ_{Rk,cr}	Characteristic bond resistance in cracked concrete C20/25	80°/50°C [MPa]	5	5,5	6	6	7,5	7,5	7,5	7,5	8
		120°/72°C [MPa]	4,5	5	5	5,5	6,5	6,5	6,5	6,5	7
		160°/100°C [MPa]	4	4,5	4,5	5	5,5	6	6	5,5	6,5
ψ_c	Increasing factor for concrete	C30/37 [-]	1,07								
		C40/50 [-]	1,08								
		C50/60 [-]	1,10								
k_{g,cr}	Factor acc. to CEN/TS 1992-4-5 sec.6.2.2.3 cracked	[-]	7,2								
k_{g,ucr}	Factor acc. to CEN/TS 1992-4-5 sec.6.2.2.3 un-cracked	[-]	10,1								
Concrete cone failure											
k_{cr}	Factor acc. to CEN/TS 1992-4-5 sec.6.2.3.1 cracked	[-]	7,2								
k_{ucr}	Factor acc. to CEN/TS 1992-4-5 sec.6.2.3.1 un-cracked	[-]	10,1								
c_{cr,N}	Critical edge distance	[mm]	1,5 • h _{ef}								
s_{cr,N}	Critical spacing	[mm]	3,0 • h _{ef}								
Splitting failure			Ø8	Ø10	Ø12	Ø14	Ø16	Ø20	Ø25	Ø28	Ø32
c_{cr,sp}	Critical edge distance for Splitting	h / h _{ef} ≥ 2,0	1,0 • h _{ef}								
		2,0 > h / h _{ef} > 1,3	2,0 • h _{ef} • (2,5 - h / h _{ef})								
		h / h _{ef} ≤ 1,3	2,4 • h _{ef}								
s_{cr,sp}	Critical spacing for Splitting	[mm]	2,0 • c _{cr,sp}								
γ₂ = γ_{inst}	Installation safety factor for Cleaning CAC ¹⁾	[-]	1,0 [1,2 for cracked]				1,2				
γ₂ = γ_{inst}	Installation safety factor for Cleaning MAC ¹⁾	[-]	1,2				-				
Displacement under Tension Load			Ø8	Ø10	Ø12	Ø14	Ø16	Ø20	Ø25	Ø28	Ø32
δ_{No}	Short term displacement un-cracked concrete	80°/50°C	0,031	0,032	0,034	0,035	0,037	0,039	0,043	0,045	0,048
		120°/72°C [mm/MPa]	0,032	0,034	0,035	0,036	0,038	0,041	0,045	0,047	0,050
		160°/100°C	0,121	0,126	0,131	0,137	0,142	0,153	0,164	0,172	0,186
δ_{N∞}	Long term displacement un-cracked concrete	80°/50°C	0,040	0,042	0,044	0,045	0,047	0,051	0,055	0,058	0,063
		120°/72°C [mm/MPa]	0,042	0,044	0,045	0,047	0,049	0,053	0,057	0,060	0,065
		160°/100°C	0,124	0,129	0,135	0,141	0,146	0,157	0,169	0,177	0,192
δ_{No}	Short term displacement cracked concrete and Seismic C1	80°/50°C	0,081	0,083	0,085	0,087	0,090	0,095	0,099	0,103	0,108
		120°/72°C [mm/MPa]	0,084	0,086	0,088	0,090	0,093	0,098	0,103	0,107	0,113
		160°/100°C	0,312	0,321	0,330	0,340	0,349	0,367	0,385	0,399	0,425
δ_{N∞}	Long term displacement cracked concrete and Seismic C1	80°/50°C	0,104	0,107	0,110	0,113	0,116	0,122	0,128	0,133	0,141
		120°/72°C [mm/MPa]	0,108	0,111	0,114	0,118	0,121	0,127	0,133	0,138	0,148
		160°/100°C	0,321	0,330	0,340	0,349	0,358	0,377	0,396	0,410	0,449

¹⁾ CAC = Cleaning with Compressed air and MAC = Cleaning with Manual Hand Pump

²⁾ f_{uk} shall be taken from the specifications of reinforcing bars

³⁾ In absence of other national regulations.

⁴⁾ Calculation of the displacement = δ_N × τ (τ = τ_{rk} / γ₂ × 1,5 × 1,4)

ANNEX IV°

Declared Performances acc. to ETA-16/0957 & ETAG001 p.1-5 - Design method acc. to TR029 or CEN/TS 1992-4
 Declared Performances acc. to ETA-16/0957 & ETAG001 Annex E - Design method acc. to TR045

ESSENTIAL CHARACTERISTICS			PERFORMANCE - REBAR								
SHEAR Steel failure			Ø8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 25	Ø 28	Ø 32
$V_{Rk,s}$	Shear Steel characteristic failure	[kN]	0,5 · $N_{Rk,s}$								
$V_{Rk,s,C1}$	Shear Steel characteristic failure Seismic C1	[kN]	0,37 · $N_{Rk,s}$								
$M_{Rk,s}^0$	Bending Moment characteristic failure	[Nm]	1,2 · $W_{el} \cdot f_{uk}^{1)}$								
$M_{Rk,s,C1}^0$	Bending Moment characteristic failure Seismic C1	[Nm]	NPD [No Performance Data]								
W_{el}	Elastic section modulus	[mm ³]	50	98	170	269	402	785	1534	2155	3217
$\gamma_{m,sV}$	Partial safety factor	[-]	1,5 ²⁾								
K_2	Ductility factor acc. to CEN/TS 1992-4-5 sec.6.3.2.1	[-]	0,8								
Concrete Pryout failure											
k	Factor in equation 5.7 of TR029	[-]	2,0								
K_3	Factor in equation 27 of CEN/TS 1992-4-5 sec.6.3.3	[-]	1,0								
$\gamma_2 = \gamma_{inst}$	Installation safety factor	[-]	1,0								
Concrete Edge failure											
l_f	Effective length of anchor	[-]	$l_f \leq \min(h_{ef}; 8 \cdot d_{nom})$								
d_{nom}	Outside diameter of anchor	[mm]	8	10	12	14	16	20	25	28	32
$\gamma_2 = \gamma_{inst}$	Installation safety factor	[-]	1,0								
Displacement under Shear Load ³⁾			Ø8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 25	Ø 28	Ø 32
δ_{V0}	Short term displacement in Concrete and Seismic C1	[mm/kN]	0,06	0,05	0,05	0,04	0,04	0,04	0,03	0,03	0,03
$\delta_{V\infty}$	Long term displacement in Concrete and Seismic C1	[mm/kN]	0,09	0,08	0,08	0,06	0,06	0,06	0,05	0,04	0,04

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ In absence of other national regulations

³⁾ Calculation of the displacement = $\delta_V \times V$ ($V = V_{Rk,s} / \gamma_2 \times 1,5 \times 1,4$)

ANNEX V°

Declared Performances acc. to ETA-16/0961 & EAD 330087-00-0601

Design method acc. to EN 1992-1-1:2004+AC:2010 and ETA-16/0961

ESSENTIAL CHARACTERISTICS			PERFORMANCE POST-INSTALLED REBAR CONNECTION											
Installation parameters			d	Ø8	Ø10	Ø12	Ø14	Ø16	Ø20	Ø22	Ø24	Ø25	Ø28	Ø32
d ₀	Nominal diameter of drill bit	[mm]		12	14	16	18	20	25	28	32	32	35	40
l _{v,MAX}	Maximum embedment depth	[mm]	see table B6 of ETA-16/0961											
l _{b,min}	Minimum anchorage length	[mm]	§ 8.6 - § 8.7 EN 1992-1-1:2004+AC2010											
l _{0,min}	Lap length	[mm]	§ 8.11 EN 1992-1-1:2004+AC2010											
α _{lb}	Amplification factor for l _{b,min} and l _{0,min}	[-]	1,0											
c ¹⁾²⁾	Minimum concrete cover min c	Without hammer drilling HD	[mm]	30 mm + 0,06·l _v ≥ 2·Ø								40 mm + 0,06·l _v ≥ 2·Ø		
		drilling Aid compr. air drilling CD	[mm]	50 mm + 0,08·l _v								60 mm + 0,08·l _v		
	With hammer drilling HD	[mm]	30 mm + 0,02·l _v ≥ 2·Ø								40 mm + 0,02·l _v ≥ 2·Ø			
		drilling Aid compr. air drilling CD	[mm]	50 mm + 0,02·l _v								60 mm + 0,02·l _v		
s _{min}	Minimum spacing	[mm]	≥ 5·Ø ≥ 50 mm											
Design values of ultimate bond resistance														
f _{bd}	Bond design value resistance "for all drilling methods for good conditions"	C12/15	[N/mm ²]	1,6										
		C16/20	[N/mm ²]	2,0										
		C20/25	[N/mm ²]	2,3										
		C25/30	[N/mm ²]	2,7										
		C30/37	[N/mm ²]	3,0										
		C35/45	[N/mm ²]	3,4										
		C40/50	[N/mm ²]	3,7										
		C45/55	[N/mm ²]	4,0										
		C50/60	[N/mm ²]	4,3										
f _{bd,c}	"for all other bond conditions"	[N/mm ²]	f _{bd} · 0,7											
FIRE EXPOSURE Design method acc. to EN 1992-1-1:2004+AC:2008														
f _{bd,fi}	Bond design value resistance Under FIRE EXPOSURE	[N/mm ²]	³⁾ f _{bd,fi} = k _{b,fi} (θ) · f _{bd} · γ _c / γ _{M,fi}											

- 1) Not allowed Diamond Drilling
- 2) The minimum concrete cover acc. EC 1992-1-1:2004+AC:2010 must be observed
- 3) With: k_{b,fi}(θ) = reduction factor under fire exposure (see graphics below)
 - f_{bd} = see table above
 - γ_c = partial safety factor acc.to EN 1992-1-1
 - γ_{M,fi} = partial safety factor acc.to EN 1992-1-2 under fire exposure

Example graph of Reduction factor k_{b,fi}(θ) for concrete classes C20/25 for good bond conditions:

